



LOBADUR®

2K Supra

ADVANCED
TECHNOLOGY

Ceramic-reinforced two-component water-based polyurethane finish for all types of timber flooring

Super durable, Supra scratch-resistant, the real Ceramic!

The most scratch-resistant water-based timber floor finish on the market - for long-lasting protection and superior film build

Do you have special requirements? So do we! Choose 2K Supra A.T. with optimised formula and benefit from an extremely resilient and durable surface. Make use of the time advantage: the sealed floor can be fully stressed after just 24 hours.

Optimized
Formula



LOBA –The best you can get from Start to Finish

Why end users are convinced of 2K Supra A.T. :

- Long-lasting flooring thanks to optimised protection against scratches and high resistance
- Full use after just 24 hours
- Very low emissions
- Increased slip resistance

Why contractors are enthusiastic about 2K Supra A.T.:

- Excellent flow and wetting properties thanks to an optimised formula
- Excellent scratch-resistance thanks to innovative ceramic reinforcement
- Excellent resilience to chemicals, friction and wear
- Can be fully stressed after 24 hours
- Very low emissions, EMICODE® EC1
- Sliding friction coefficient > 0.5 according to DIN 18032 for sports flooring

Special feature

The ceramic-reinforced Timber flooring lacquer provides an extremely scratch-resistant surface and offers long-lasting protection.

Range of use

Perfect for demanding and high-traffic floors, such as in restaurants, shops and sports halls (**Fiba approved**). Suitable for parquet, wooden floors as well as cork, linoleum and PVC coverings. Achieves the dynamic coefficient of friction as per DIN 18032 for sports flooring. For extremely heavy use.

Application


- Professionally sand and de-dust the substrate
- Apply primer as specified in TI
- First coat of 2K Supra A.T. with the LOBAT00L Deluxe 120 roller or Microfibre 100–120 roller
- Intermediate sanding after 8–10 hours with LOBASAND P180 perforated pad or finer for the semi-matte version, or the P120 perforated pad for the matte version
- Second coat of 2K Supra A.T. with the LOBAT00L Deluxe 120 roller or Microfibre 100–120 roller
- Consumption quantity per application: 100-120 g/m² with the LOBAT00L Deluxe 120 roller or 80-100 g/m² with the Microfibre 100-120 roller



Article no. 11465

Available in matte and semi-matte (5kg)

GISCODE W3/DD+



LOBA is always at your side and ensures your success with both advice and action. Our experienced application specialists will advise you personally with your projects. Our competent service team is quickly on hand if you need practical support directly on site. So you can be on the safe side right from the start and know who you can rely on at all times.

Do you have any questions? Please do not hesitate to contact us:

Please observe the detailed technical information, processing instructions and set-up recommendation.

Technical information



LOBA GmbH & Co. KG

Leonberger Str. 56–62 | 71254 Ditzingen | Germany | Tel: +49 7156 357-0 | Australia 03) 94623230 | www.loba.com.au